

19



Europäisches Patentamt  
European Patent Office  
Office européen des brevets



11 Publication number: **0 491 985 A1**

12

## EUROPEAN PATENT APPLICATION

21 Application number: **90125464.9**

51 Int. Cl.<sup>5</sup>: **C08L 67/02, //(C08L67/02,9:02, 23:08),(C08L67/02,55:02,23:08)**

22 Date of filing: **24.12.90**

43 Date of publication of application:  
**01.07.92 Bulletin 92/27**

84 Designated Contracting States:  
**DE ES FR GB IT NL**

71 Applicant: **GENERAL ELECTRIC COMPANY**  
**1 River Road**  
**Schenectady, N.Y. 12151(US)**

72 Inventor: **Goff, Leslie Joe**  
**General Electric Plastic B.V., P.O. Box 117**  
**NL-4600 AC Bergen op Zoom(NL)**  
Inventor: **Van Oosterbosch, Cornelis Jacobus**  
**Maria**  
**General Electric Plastic B.V., P.O. Box 117**  
**NL-4600 AC Bergen op Zoom(NL)**  
Inventor: **Van der Meer, Roelof**  
**General Electric Plastic B.V., P.O. Box 117**  
**NL-4600 AC Bergen op Zoom(NL)**

74 Representative: **Schüler, Horst, Dr. et al**  
**General Electric Praunheimer Landstrasse**  
**50**  
**W-6000 Frankfurt 90(DE)**

54 **Impact modified polybutylene terephthalate.**

57 The invention provides a polybutylene terephthalate composition which contains an impact modifier in an impact modifying amount, wherein the impact modifier is a synergistic mixture of (1) an acrylonitrile and butadiene unit-containing polymer and (2) a terpolymer of (a) ethylene, (b) a lower alkylacrylate and (c) a monomer which contains a heterocycle containing one oxygen atom as the hetero-atom.

EP 0 491 985 A1

This invention relates to impact modified polybutyl ne terephthalate.

Poly(butylene terephthalat ) (her inafter abbreviated as PBT) is a thermoplastic material having good chemical resistance and relatively good flow. PBT possesses a glass transition temperatur of approxi-  
 5 mately 40-50° C. Therefor , in order to achieve the toughness needed for most practical purposes, an impact modifier should be added to the PBT. Several impact modifiers have been used for PBT previously, including ABS which is customarily used in PBT compositions not containing polycarbonate. A special kind  
 10 of ABS-graft polymers has been disclosed as impact modifiers for PBT in EP-A-0022216. Also acrylonitrile-butadiene copolymers have been used for this purpose and according to Fowler, M.E. Keskkula, H, Paul, D.R., Polymer, 28, p.1703-1711 (1987) copolymers from acrylonitrile and cis-butadiene provide a low  
 15 temperature ductility. A further problem is that for some uses good charpy notched impact strength (hereinafter sometimes abbreviated as CNI) is desired. For CNI there is a very strong concentration effect caused by the notch in this test, and therefore the material strain is constrained entirely in the middle of the specimen bar, and around the fracture surface, as discussed by Polato, F., J.Mat.Sci. 20, p. 1455-1465, (1985). A CNI of at least 25 J/m which is needed for some purposes, can be obtained with high percentages  
 20 of ABS polymers or the like, but in that case the viscosities suffer severely. Accordingly, there is a need for an impact modifier for PBT which in moderate contents provides the desired high CNI values.

Surprisingly it has now been found that a group of specific terpolymers has somewhat better impact modifying properties than the acrylonitrile-butadiene copolymers and terpolymers, and more particularly that combinations of these specific terpolymers with the acrylonitrile-butadiene copolymers and terpolymers  
 25 show a completely unexpected synergistic action so that with these combinations CNI values at room temperature of 25 J/m<sup>2</sup> and above can easily be attained.

Thus, the invention provides an impact modified polybutylene terephthalate composition containing an impact modifier in an impact modifying amount, wherein the impact modifier is a synergistic mixture of (1) an acrylonitrile and butadiene units-containing polymer and (2) a terpolymer of (a) ethylene, (b) a lower alkyl  
 30 acrylate and (c) a monomer which contains a heterocycle containing one oxygen atom as the hetero-atom.

Component (1) is one of the usual impact modifiers for this purpose and can be an acrylonitrile-butadiene copolymer or one of the several ABS polymers, for instance of the graft or core-shell type.

Component (2) is a terpolymer wherein the greater parts of the monomers (55-75 %) is derived from ethylene, 20-30 % of the monomers is derived from a lower alkyl acrylate, and 5-15 % of the monomers is  
 35 derived from monomer (c), it being understood that the sum of the three percentages is 100. By "lower alkyl acrylate" is understood here a C1-4 alkyl ester of acrylic or methacrylic acid.

Component (c) can contain the heterocycle as part of the main polymer chain or in a pendant group. An example of the first possibility is maleic anhydride, and a particularly suitable pendant heterocyclic group is the glycidyl residue. A particularly preferred monomer (c) is glycidyl methacrylate.

Some of these terpolymers are commercially available and all these terpolymers will be produced according to well-known processes.

The weight ratio between components (1) and (2) can vary within wide limits, but is preferably 10:1 to 1:1.5 and more preferably 4:1 to 1:1.

As mentioned hereinabove, the impact modifying synergistic mixture should be used in an impact  
 40 modifying amount. This amount can also vary within wide limits, and will also depend on the influence on other physical properties which can be tolerated. In general the synergistic combination of the present invention will be used in a total amount of 6-20 weight percent of the composition. Amounts of less than 6 % usually will not have sufficient impact modifying effect and amounts of substantially over 20 % will tend to unduly affect other desirable properties. Preferably the amount of the synergistic combination is 10-15 %  
 45 of the entire composition.

Of course, the compositions of the invention may contain minor amounts of further usual additives, such as anti-oxidants, fillers, reinforcing fillers, stabilizers, dyes and pigments, plasticizers, mold release agents, lubricants, antistatic agents, flame retardants and the like.

Th following examples are intended to elucidat the present invention. However, the invention is not  
 50 limited by these examples in any way.

#### Example 1

PBT compositons were prepared with various impact modifiers, and th physical properties of the  
 55 compositions w r measured. The results are as follows:

Table 1

5	Composition	1	2	3	4	5	6	7	8
	PBT	89.7	84.7	79.7	75.7	89.7	89.7	89.7	89.7
10	Hindered								
	Phenol	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2
	Sandostab								
15	4020a)	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1
	ABS	10	15	20	25	-	-	-	-
	core-shell								
20	polymer b)	-	-	-	-	10	-	-	-
	core-shell1								
	polymer c)	-	-	-	-	-	10	-	-
	Terpolymer A <sup>d)</sup>	-	-	-	-	-	-	10	-
25	Terpolymer B <sup>e)</sup>	-	-	-	-	-	-	-	10

30

35

40

45

50

55

Physical data	1	2	3	4	5	6	7	8
Ten.modulus (MPa)	2210	2110	1937	1688	2175	2127	2264	2114
Ten.Str. Yield (MPa)	46.7	46.3	41.9	37.6	49.8	49.0	49.0	48.0
Elong. Break (%)	195	215	255	240	154	157	121	61
INI at RT (J/m)	525	695	808	850	105	125	80	605
CNI at RT (kJ/m <sup>2</sup> )	8.8	22.3	28.4	31.3	5.4	8.3	9.8	14.5
MVI (250°C/50N) (cm <sup>3</sup> /10')	21.4	9.7	5.2	2.4	23.4	22.6	--	5.9

a) pentaerythritol-tetrakis(3-dodecylthiopropionate)

b) core-shell polymer having 80 % butadiene-polystyrene core and 20 % poly-MMA shell

c) core-shell polymer as b), but with core-shell ratio of 90:10

d) Terpolymer of ethylene with 26 % ethylacrylate and 7 % maleic anhydride;

e) Terpolymer of ethylene with 26 % ethylacrylate and 7 % glycidylmethacrylate

INI means Izod notched impact strength; RT means room temperature; CNI means charpy notched impact strength and MVI means melt viscosity index.

These screening tests show that when using the ABS polymer as impact modifier, CNI values of over 25 kJ/m<sup>2</sup> can only be obtained with high percentages of the ABS with concomitant unacceptably low MVI values. 10 % of terpolymer (A) gives a clearly higher CNI value than the same amount of the ABS, and terpolymer B in a content of 10 % gives a considerably higher CNI value. The two other tested substances give worse results than the ABS, when used in the same amount of 10 %.

#### Example 2

Combinations of the ABS and the terpolymer B of Example 1 were tested in three different ratios. The results are given in the following Table.

Table 2

Composition	I	II	III
PBT	84.7	84.7	84.7
Terpolymer B	7.5	5	3
ABS	7.5	10	12
Hindered phenol	0.2	0.2	0.2
Sandostab 4020	0.1	0.1	0.1
Results	I	II	III
Ten.mod (MPa)	1790	1860	1950
Ten.Str. Yield (MPa)	47.3	42.2	42.8
Elong. (%)	230	170	130
INI at RT (J/m)	866	854	802
CNI at RT (kJ/m <sup>2</sup> )	30.5	29.4	29.9
MVI (250°C/50N) (cm <sup>3</sup> /10')	10.7	12.2	10.9

As appears from these results the desired CNI values of over 25 kJ/m<sup>2</sup> are easily attained with the three tested mixtures. It should be remarked in this respect that terpolymer B is a more expensive material than the ABS so that it is economically very interesting that approximately the same CNI values were obtained over the examined range of ABS/terpolymer B ratios of 1:1 till 4:1. The commercial product used as a comparison is believed to contain also 15 % of impact modifier.

The reason for the unexpected synergism of the present invention is not known with certainty.

All patent (applications) mentioned herein are herewith incorporated by reference.

#### Claims

1. Polybutylene terephthalate composition containing an impact modifier in an impact modifying amount, wherein the impact modifier is a synergistic mixture of (1) an acrylonitrile and butadiene units-containing polymer and (2) a terpolymer of (a) ethylene, (b) a lower alkylacrylate and (c) a monomer which contains a heterocycle containing one oxygen atom as the hetero-atom.
2. Polybutylene terephthalate composition according to claim 1, wherein component (1) is a copolymer of acrylonitrile and butadiene.
3. Polybutylene terephthalate composition according to claim 1, wherein component (1) is an ABS polymer.
4. Polybutylene terephthalate composition according to claims 1-3, wherein monomer (c) is glycidyl methacrylate.
5. Polybutylene terephthalate composition according to claims 1-3, wherein monomer (c) is maleic

anhydride.

6. Polybutylene terephthalate composition according to claims 1-5, wherein the weight ratio of component (1) and component (2) is 10:1 to 1:1.5.

5

7. Polybutylene terephthalate composition according to claim 6, wherein the ratio is 4:1 tot 1:1.

8. Polybutylene terephthalate composition according to claim 1 comprising further usual additives.

10 9. Polybutylene terephthalate composition according to any claims 1-8, wherein the synergistic mixture comprises 6-20 weight percent of the entire composition.

10. Polybutylene terephthalate composition according to claim 9, wherein the synergistic mixture comprises 10-15 weight percent of the entire composition.

15

11. Polybutylene terephthalate composition according to any of claims 1-10 having a charpy notched impact strength at room temperature of at least 25 J/m<sup>2</sup>.

20

25

30

35

40

45

50

55



European Patent  
Office

EUROPEAN SEARCH REPORT

Application Number

EP 90 12 5464

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl.5)
D,A	EP-A-0 022 216 (BAYER) * Claims 1-10 * ---	1,3,8	C 08 L 67/02 // (C 08 L 67/02
A	FR-A-2 311 808 (E.I. DU PONT) * Claims 1,32; page 12, line 40 - page 13, line 2 * ---	1,4,8	C 08 L 9:02 C 08 L 23:08 ) (C 08 L 67/02 C 08 L 55:02 C 08 L 23:08 )
A	FR-A-2 617 176 (SOCIETE CHIMIQUE DES CHARBONNAGES) * Claims 1-3; page 2, lines 33-36 * ---	1,5,8	
A	EP-A-0 335 394 (TOYOTA JIDOSHA K.K.) * Claims 1-12; page 9, lines 13-46 * -----	1,3,8	
			TECHNICAL FIELDS SEARCHED (Int. Cl.5)
			C 08 L
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 27-08-1991	Examiner DECOCKER L.
CATEGORY OF CITED DOCUMENTS		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons ----- & : member of the same patent family, corresponding document	
X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document			

EPO FORM 1503 (03.82) (P0601)